

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
31 July 2003 (31.07.2003)

PCT

(10) International Publication Number
WO 03/062085 A1

- (51) International Patent Classification⁷: **B65D 65/46, B23K 26/40**
- (74) Agent: **BARKER BRETTELL**; St John's Innovation Centre, Cowley Road, Cambridge CB4 0WS (GB).
- (21) International Application Number: **PCT/GB03/00276**
- (22) International Filing Date: **24 January 2003 (24.01.2003)**
- (25) Filing Language: **English**
- (26) Publication Language: **English**
- (30) Priority Data:
0201856.2 **26 January 2002 (26.01.2002)** **GB**
- (71) Applicants (*for all designated States except US*): **AQUA-SOL LIMITED** [GB/GB]; Writtle College Campus, Chelmsford, Essex CM1 3WM (GB). **HERFURTH LASER TECHNOLOGY LIMITED** [GB/GB]; Barclays Venture Centre, University of Warwick Science Park, Sir William Lyons Road, Coventry, Warwickshire CV4 7EZ (GB).
- (72) Inventors; and
- (75) Inventors/Applicants (*for US only*): **EDWARDS, David, Brian** [GB/GB]; 8D, Long Lane, Aston End, Stevenage, Herts SG2 7HG (GB). **BRYDEN, Brian, George** [GB/GB]; 32 Michaelmas Road, Coventry, Warwickshire CV3 6HG (GB).
- (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Published:**
- *with international search report*
 - *before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments*
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

(54) Title: **CUTTING OR PERFORATING WATER-SOLUBLE FILM**

(57) Abstract: A process for cutting or perforating a water-soluble or water-dispersible film or stack of films in the form of a web comprising a plurality of compartments by which each compartment is cut or perforated by applying a laser beam to the film or stack of films. The process for producing a water-soluble or water-dispersible container containing a composition comprises: a. producing a base web water-soluble or water-dispersible film containing a plurality of pockets; b. filling each pocket with a composition; c. sealing the pockets with a top web water-soluble or water-dispersible film to produce closed containers; and d. separating at least one container from the plurality of containers by cutting or perforating the combined web with a laser beam.

WO 03/062085 A1

-1-

CUTTING OR PERFORATING WATER-SOLUBLE FILM

The present invention relates to a process for
5 cutting or perforating a polyvinyl alcohol (PVOH) film,
in particular laminates and stacks thereof.

PVOH film is finding an increasingly large number of
uses. Many PVOH films are water-soluble, and can be used
10 to prepare containers containing compositions such as
laundry detergents, hazardous compositions, and
ingestible compositions. Examples of such containers are
described in, for example, WO 00/55068.

15 PVOH film is difficult to process. It is water
soluble and, to a certain extent, hygroscopic. It is
sensitive to changes in temperature and changes in
humidity. In addition it has a high tensile strength,
for example many times greater than that of polyethylene,
20 but lacks rigidity as compared to other films such as
those made from PVC, polypropylene and polystyrene.

These factors make it difficult to cut PVOH
films satisfactorily. PVOH has, up to now, only been
25 moderately successfully cut on an industrial scale using
flying knives, crush cut roller knives or precision punch
cutting systems. Even these cutting methods have proved
to be problematic. The tensile and elongation properties
of the PVOH film mean that considerable heat is generated
30 during the cutting. This, coupled with the variable
nature of its physical properties due to its sensitivity
to temperature and humidity changes, means that it is

-2-

difficult to cut PVOH film reliably and repeatedly. This can easily be demonstrated by trying to tear a perforated PVOH film along its line of perforations. The stretch characteristics of the film mean that the film is almost
5 always distorted, no matter how much care is taken when tearing the film along the perforations. Furthermore, jamming of mechanical cutting means can easily occur. Regular maintenance is therefore required to keep cutting edges clean and clear from heated PVOH debris. If this
10 debris is not removed, it can cause jams or damage the cutting edges, both of which can lead to major production delays. It has also been found that the knives quickly lose their cutting edge and have to be sharpened or replaced, again leading to increased down-time of the
15 cutting apparatus.

Furthermore, precision punches are heavy and expensive items of equipment which require substantial support and hence careful consideration as to their
20 placement in a production line. This generally means that a production line such as a thermoforming apparatus has to be extended in order to accommodate such a punch.

This has been found to be a particular disadvantage
25 when cutting PVOH containers from a line of, or a two-dimensional array of, containers, for example as produced by a continuous motion or an intermittent motion thermoforming apparatus. The gap between each container must be fairly large in order to ensure that the
30 containers themselves are not damaged when cutting or perforating (by mechanical means) the film between them due to localised stretching of the web. Typically, such

-3-

thermoformed PVOH containers are designed to have a seal width of 3.0-7.0mms and the distance between the outer periphery of the sealed parts of a stack of films around neighbouring containers ("the gap" between containers) is

5 5.0-15.0mms

We have found a method of cutting or perforating PVOH film or a stack of PVOH films which overcomes the above disadvantages.

10

The present invention provides a process for cutting or perforating a water-soluble or water-dispersible film or stack of films in the form of a web comprising a plurality of containers by which at least one container

15 is cut or perforated by applying a laser beam to the film or stack of films.

Thus one or more layers of PVOH film are cut or perforated utilising a focused laser beam of a wavelength

20 which is absorbed by PVOH. Typically such lasers operate in the infra-red range of the spectrum between 0.7 and 20 μm .

The process allows the web to be cut or perforated

25 extremely close to the seal of the container. Thus the distance between the outer periphery of the sealed stack of films around neighbouring containers is substantially less than that required for mechanical cutting or perforation.

30

Laser cutting has been the subject of many publications including, for example:

-4-

The Laser Institute of America Guide to Laser
Cutting, published by the Laser Institute of
America: ISBN 0-912035-17-X
and

5 CO2 Laser Cutting, published by Springer Verlag:
ISBN 1-85233-047-3

The present invention additionally provides a process for
producing a water-soluble or water-dispersible container.
10 containing a composition which comprises:

- a. producing a base web water-soluble or water-
dispersible film containing a plurality of pockets;
- b. filling each pocket with a composition;
- c. sealing the pockets with a top web water-
15 soluble or water-dispersible film to produce closed
containers; and
- d. separating at least one container from the
plurality by cutting the top and bottom web films
with a laser beam.

20

The present invention also provides for the use of a
laser beam to cut or perforate one or more layers of PVOH
film.

25

By "cutting", we mean a process in which a laser
beam is drawn over a surface of one or more layers of
PVOH film, by moving the laser beam, by moving the film
either in continuous motion or in intermittent motion or
by a combination of moving the laser beam and moving the
30 film. The cut may be of any length and may separate at
least one piece of PVOH film from the remainder, although
this is not essential.

By "perforating", we mean a process in which a series of holes, short cuts or serrations are formed in one or more layers of PVOH film, particularly at least 3, 5 or 10
5 holes or cuts, in a pattern. The pattern may be any shape, for example a straight line or a curved line, whether producing a complete periphery or not. The perforations assist the subsequent tearing of the film, for example by hand.

10

The method of the present invention eliminates the adverse effect of localised heating of the film around the cutting area. Although by use of this invention, elevated temperatures may still be generated around the
15 cut portion of the film, this no longer matters since the heated film has no knife or other mechanical device to which to stick. Furthermore, the success of the method is entirely independent of the tensile and elongation properties of the film.

20

Additionally, since the laser beam can be precisely controlled, for example by appropriate software, it can be used to cut or perforate between containers even when the distance between the outer periphery of the sealed
25 stack of films around neighbouring containers ("the gap") is substantially less than that required for mechanical cutting or perforating. This is because the laser cutting or perforating operation will no longer need to take into account the variable effects of web stretch or
30 wander. In the limiting case, although this is not preferred, we have shown that the gap between containers may be eliminated altogether.

-6-

Laser heads can be supported easily almost anywhere on a production line, with the beam delivered through an appropriate beam delivery system such as a galvanometer based laser scanning head. This has considerable practical advantage in that the production line can be shortened, thus possibly enabling a line to be installed where it could not if a precision punch or other mechanical means were used for cutting or perforating.

10

The process of the present invention can use a variety of laser systems but typically a medium powered CO2 laser and galvanometer based beam delivery system would be used in this application. Successful results have been obtained with a 25 watt CO2 laser operating at a wavelength of 10.6 μ m and a laser head of 200mm focal length. The laser head may be integral with the remainder of the laser, or may be separate and linked to the remainder of the laser by a fibre optic cable.

20

On thin PVOH film applications, very high speeds can be anticipated with medium range laser powers when cutting on a continuous basis. Perforating can be controlled by the pulse repetition frequency of the laser.

25

The PVOH film may be produced by, for example, casting or blowing. The film may be a single film. However, it is possible for the film to be in the form of a laminate, for example with another PVOH film or with another water-soluble polymer such as a cellulose derivative such as hydroxypropyl methyl cellulose (HPMC), poly(vinylpyrrolidone) (PVP), poly(acrylic acid) or an

30

-7-

ester thereof, poly(maleic acid) or an ester thereof, or gelatin. Copolymers of any of the above may also be used. The laminate may, for example, have 2, 3, 4, 5 or 6 or more layers.

5

The PVOH is preferably water-soluble (which term is taken to include water-dispersible), for example in cold or in warm water. By choosing an appropriate PVOH polymer, it is possible to ensure that it dissolves in a prescribed time at a desired temperature. Thus, for example, the PVOH film may be selected to be soluble in cold water (20°C or less), but may be selected to be insoluble in cold water and only become soluble in warm or hot water having a temperature of, for example, 30°C, 40°C, 50°C or even 60°C. The PVOH may be partially or fully alcoholised or hydrolysed. For example it may be from 40 to 100%, preferably from 70 to 92%, more preferably about 88%, alcoholised or hydrolysed. The degree of hydrolysis is known to influence the temperature at which the PVOH will dissolve in water. Modified PVOH polymers such as ethoxylated PVOH may also be used.

The PVOH film may consist essentially of, or consist of, PVOH. It is possible for suitable additives such as plasticisers, lubricants and colouring agents to be added. Components which modify the properties of the polymer may also be added. Plasticisers are generally used in an amount of up to 20 wt%, for example from 10 to 20 wt%. Lubricants are generally used in an amount of 0.5 to 5 wt%. The PVOH is therefore generally present in an amount of from 75 to 84.5 wt%. Suitable plasticisers

-8-

are, for example, pentaerythritols such as depentaerythritol, sorbitol, mannitol, glycerine and glycols such as glycerol, ethylene glycol and polyethylene glycol. Solids such as talc, stearic acid, magnesium stearate, silicon dioxide, zinc stearate or colloidal silica may be used as lubricants.

It is also possible to include one or more particulate solids in the film in order to accelerate the rate of dissolution thereof. Dissolution of the solid in water is sufficient to cause an acceleration in the break-up of the film, particularly if a gas is generated.

Examples of such solids are alkali and alkaline earth metal, such as sodium, potassium, magnesium and calcium, bicarbonate and carbonate, in conjunction with an acid. Suitable acids are, for example, acidic substances having carboxylic or sulfonic acid groups or salts thereof. Examples are cinnamic, tartaric, mandelic, fumaric, maleic, malic, palmoic, citric and naphthalene disulfonic acids, as free acids or as their salts, for example with alkali or alkaline earth metals.

The film may have any desired thickness. A preferred thickness is 20 to 150 μm , more preferably 30 to 100 μm , especially 40 to 90 μm , more especially 50 to 80 μm and most especially 60 to 80 μm . A laminated film may also be used. A suitable thickness of the laminate is 30 to 300 μm , more preferably 40 to 200 μm , especially 40 to 100 μm .

-9-

The PVOH film may be unoriented, mono-axially oriented or bi-axially oriented. In a laminate, each film layer may independently be unoriented, mono-axially oriented or bi-axially oriented. If more than one film
5 in the laminate is oriented, they may have the same orientation, or their planes of orientation may be different if desired. The final laminate may also be unoriented, mono-axially oriented or bi-axially oriented. Orientation may be provided by, for example, stretching
10 each film before it is laminated or by stretching the laminate after it is formed.

Lamination may be carried out by any desired process. For example, lamination can be carried out
15 before the laminate is further processed. Thus the films making up the film stack may be heated to adhere them together. An adhesive layer may also be provided.

Lamination may be assisted by the use of pressure or
20 vacuum. If two adjacent films are soluble in the same solvent, that solvent may be applied to one or both adjacent surfaces to ensure adhesion. If the films are water-soluble, a suitable solvent is water or an aqueous solution of the polymers making up the films. For
25 example, if the PVOH is water-soluble, a suitable solvent is an aqueous solution of PVOH. The adhesive may be applied, for example, by casting or by printing. Desirably a pattern of adhesive is applied, such as a stipple pattern.

30

It is also possible for lamination to be carried out simultaneously with another process. For example,

-10-

lamination can occur in a thermoforming mould. This process allows for the production of a thermoformed, laminated film in one step, avoiding the use of an additional step using heating or adhesive, along with pressure or vacuum, to laminate the films. This reduces capital expenditure and other costs, as well as reducing complexity and production time, as compared with processes in which the laminate is pre-formed.

10 In a preferred embodiment of the invention, the PVOH containers are in the form of a web comprising a plurality of compartments and are cut or perforated between at least two of the compartments. The compartments may, for example, be provided by vacuum forming or thermoforming a base web PVOH film and sealed by placing a top web film on top of the filled pocket and sealing the top web film to the base web film making up the pocket, for example by heat sealing. Such a process is disclosed, for example, in WO 00/55068. Other processes for making water-soluble containers include, for example, vertical form-fill-sealing, horizontal form-fill-sealing and processes providing pillow packs.

The container is desirably water-soluble so that it can simply be added to an aqueous environment where it will dissolve to release its contents.

A suitable thermoforming temperature for PVOH or ethoxylated PVOH is, for example, from 90 to 130°C especially 90 to 120°C. A suitable forming pressure is, for example, 60 to 138 kPa (10 to 20 p.s.i.), especially 69 to 103 kPa (10 to 15 p.s.i.). A suitable forming

-11-

vacuum is 0 to 4 kPa (0 to 20 mbar), especially 0 to 2 kPa (0 to 20 mbar). A suitable dwell time is, for example, 0.4 to 2.5 seconds, especially 1.5 to 2.0 seconds .

5

One skilled in the art can choose an appropriate temperature, pressure or vacuum and dwell time, for example to achieve a laminate of the desired integrity during simultaneous thermoforming and lamination. The amount of vacuum or pressure used depends on the thickness and composition of the film. While desirably conditions are chosen within the above ranges, it is possible to use one or more of these parameters outside the above ranges, although it may be necessary to compensate by changing the values of the other parameters.

The top web film in a thermoforming or vacuum forming process is preferably water-soluble. The base web film forming the pocket and the top web film may be manufactured from the same or different compositions. The top web or the bottom web film may be a single film or a laminate. At least one, and preferably both, of the films making up the container is based upon PVOH or other water-soluble polymers.

The top web film desirably has a thickness which is less than that of the base web film making up the pocket because it will not generally be thermoformed so localised thinning of the sheet will not occur. It is also desirable to have a thickness which is less than that of the film stack to ensure a sufficient heat

-12-

transfer through the films to soften the base web, for example during heat sealing. The thickness of the covering film will generally be from 20 to 160 μm , preferably from 40 to 100 μm .

5

The films may be sealed together by any suitable means, for example by means of an adhesive or by heat sealing or by a combination thereof.

10

The composition may be any composition which is intended to be released in an aqueous environment if the container is water-soluble. Thus, for example, it may be a pesticidal composition such as a biocidal composition or a plant protection agent (for instance an insecticide, fungicide, herbicide, acaricide, or nematocide), a plant growth regulator, or a plant nutrient. It may be a hazardous composition which is potentially toxic or damaging or detrimental to health or the environment. It may be a non-hazardous or ingestible composition, for example, a pharmaceutical or nutraceutical composition. Such compositions are generally packaged in quantities of from 0.01 g to 7 kg, preferably 0.1g to 2 kg, when in solid form. When in liquid or gelled form, such compositions are generally packaged in amounts of from 1 ml to 10 litres, preferably 0.1 to 2.0 litres, especially from 0.1 to 1.0 litres.

15

20

25

30

The composition may also be a fabric care, surface care or dishwashing composition. Thus, for example, it may be a dishwashing, water-softening, laundry or detergent composition, or a rinse aid. Such compositions may be suitable for use in a domestic washing machine.

-13-

The composition may also be a disinfectant, antibacterial or antiseptic composition, or a refill composition for a trigger-type spray. Such compositions are generally packaged in amounts of from 5 to 100 g, especially from 15 to 40 g. For example, a dishwashing composition may weigh from 15 to 30 g, a water-softening composition may weigh from 15 to 40 g, and a laundry composition may weigh from 15 to 40 g.

10 The composition(s) may be a solid. For example, it may be a particulate or granulated solid, or a tablet. It may also be a liquid, which may be thickened or gelled if desired. The liquid composition may be non-aqueous (i.e. anhydrous) or aqueous, for example comprising less than or more than 5 wt% total or free water (not a very clear example). An anhydrous composition generally contains less than 1 wt%, preferably less than 0.5 wt% water. The composition may have more than one phase. For example it may comprise an aqueous composition and a liquid composition which is immiscible with the aqueous composition. It may also comprise a liquid composition and a separate solid composition, for example in the form of a ball, or pill or speckles. The liquid composition may be thickened or gelled.

25

If the composition is an aqueous liquid having a relatively high water content, for example above 5 wt% water, it may be necessary to take steps to ensure that the liquid does not attack the water-soluble polymer if it is soluble in cold water, or water up to a temperature of, say, 35°C. Steps may be taken to treat the inside surfaces of the container, for example by coating it with

-14-

suitable protective agents, or to adapt the composition to ensure it does not dissolve the polymer. For example, it has been found that ensuring the composition has a high ionic strength or contains an agent which minimises water loss through the walls of the container will prevent the composition from dissolving the film wall of the container from the inside. This is described in more detail in EP-A-518,689 and WO 97/27,743.

10 The containers produced by the process of the present invention may, if desired, have a maximum dimension of 50 cm, excluding any flanges. For example, a container may have a length of 1 to 5 cm, especially 3.5 to 4.5 cm, a width of 1.5 to 3.5 cm, especially 2 to 15 3 cm, and a height of 1 to 2 cm, especially 1.25 to 1.75 cm.


Examples of surface care compositions are those used in the field of surface care, for example to clean, treat or polish a surface. Suitable surfaces are, for example, 20 household surfaces such as worktops, as well as surfaces of sanitary ware, such as sinks, basins and lavatories. The ingredients of each composition depend on the use of the composition. Thus, for example, the composition may contain surface active agents such as an anionic, non- 25 ionic, cationic, amphoteric or zwitterionic surface active agents or mixtures thereof.

Examples of anionic surfactants are straight-chained or branched alkyl sulfates and alkyl polyalkoxylated 30 sulfates, also known as alkyl ether sulfates. Such

-15-

surfactants may be produced by the sulfation of higher C₈-C₂₀ fatty alcohols.

Examples of primary alkyl sulfate surfactants are those of formula:



wherein R is a linear C₈-C₂₀ hydrocarbyl group and M is a water-solubilising cation. Preferably R is C₁₀-C₁₆ alkyl, for example, C₁₂-C₁₄, and M is alkali metal such as lithium, sodium or potassium.

10

Examples of secondary alkyl sulfate surfactants are those which have the sulfate moiety on a "backbone" of the molecule, for example those of formula:



15 wherein m and n are independently 2 or more, the sum of m+n typically being 6 to 20, for example 9 to 15, and M is a water-solubilising cation such as lithium, sodium or potassium.

20 Especially preferred secondary alkyl sulfates are the (2,3) alkyl sulfate surfactants of formulae:



for the 2-sulfate and 3-sulfate, respectively. In these
25 formulae x is at least 4, for example 6 to 20, preferably 10 to 16. M is cation, such as an alkali metal, for example lithium, sodium or potassium.

Examples of alkoxyated alkyl sulfates are ethoxylated alkyl sulfates of the formula:



wherein R is a C₈-C₂₀ alkyl group, preferably C₁₀-C₁₈ such as a C₁₂-C₁₆, n is at least 1, for example from 1 to 20,

-16-

preferably 1 to 15, especially 1 to 6, and M is a salt-forming cation such as lithium, sodium, potassium, ammonium, alkylammonium or alkanolammonium. These compounds can provide especially desirable fabric cleaning performance benefits when used in combination with alkyl sulfates.

The alkyl sulfates and alkyl ether sulfates will generally be used in the form of mixtures comprising varying alkyl chain lengths and, if present, varying degrees of alkoxylation.

Other anionic surfactants which may be employed are salts of fatty acids, for example C₈-C₁₈ fatty acids, especially the sodium or potassium salts, and alkyl, for example C₈-C₁₈, benzene sulfonates.

Examples of non-ionic surfactants are fatty acid alkoxyates, such as fatty acid ethoxyates, especially those of formula:



wherein R is a straight or branched C₈-C₁₆ alkyl group, preferably a C₉-C₁₅, for example C₁₀-C₁₄, alkyl group and n is at least 1, for example from 1 to 16, preferably 2 to 12, more preferably 3 to 10.

The alkoxyated fatty alcohol non-ionic surfactant will frequently have a hydrophilic-lipophilic balance (HLB) which ranges from 3 to 17, more preferably from 6 to 15, most preferably from 10 to 15.

-17-

Examples of fatty alcohol ethoxylates are those made from alcohols of 12 to 15 carbon atoms and which contain about 7 moles of ethylene oxide. Such materials are commercially marketed under the trademarks Neodol 25-7 and Neodol 23-6.5 by Shell Chemical Company. Other useful Neodols include Neodol 1-5, an ethoxylated fatty alcohol averaging 11 carbon atoms in its alkyl chain with about 5 moles of ethylene oxide; Neodol 23-9, an ethoxylated primary C₁₂-C₁₃ alcohol having about 9 moles of ethylene oxide; and Neodol 91-10, an ethoxylated C₉-C₁₁ primary alcohol having about 10 moles of ethylene oxide.

Alcohol ethoxylates of this type have also been marketed by Shell Chemical Company under the Dobanol trademark. Dobanol 91-5 is an ethoxylated C₉-C₁₁ fatty alcohol with an average of 5 moles ethylene oxide and Dobanol 25-7 is an ethoxylated C₁₂-C₁₅ fatty alcohol with an average of 7 moles of ethylene oxide per mole of fatty alcohol.

20

Other examples of suitable ethoxylated alcohol non-ionic surfactants include Tergitol 15-S-7 and Tergitol 15-S-9, both of which are linear secondary alcohol ethoxylates available from Union Carbide Corporation. Tergitol 15-S-7 is a mixed ethoxylated product of a C₁₁-C₁₅ linear secondary alkanol with 7 moles of ethylene oxide and Tergitol 15-S-9 is the same but with 9 moles of ethylene oxide.

Other suitable alcohol ethoxylated non-ionic surfactants are Neodol 45-11, which is a similar ethylene oxide condensation products of a fatty alcohol having 14-

30

-18-

15 carbon atoms and the number of ethylene oxide groups per mole being about 11. Such products are also available from Shell Chemical Company.

5 Further non-ionic surfactants are, for example, C₁₀-C₁₈ alkyl polyglycosides, such as C₁₂-C₁₆ alkyl polyglycosides, especially the polyglucosides. These are especially useful when high foaming compositions are desired. Further surfactants are polyhydroxy fatty acid
10 amides, such as C₁₀-C₁₈ N-(3-methoxypropyl) glycamides and ethylene oxide-propylene oxide block polymers of the Pluronic type.

Examples of cationic surfactants are those of the
15 quaternary ammonium type.

The total content of surfactants in the composition is desirably 60 to 95 wt%, especially 75 to 90 wt%. Desirably an anionic surfactant is present in an amount
20 of 50 to 75 wt%, the non-ionic surfactant is present in an amount of 5 to 20 wt%, and/or the cationic surfactant is present in an amount of from 0 to 20 wt%. The amounts are based on the total solids content of the composition, i.e. excluding any solvent which may be present.

25

The composition, particularly when used as laundry washing or dishwashing composition, may also comprise enzymes, such as protease, lipase, amylase, cellulase and peroxidase enzymes. Such enzymes are commercially
30 available and sold, for example, under the registered trade marks Esperesc, Alcalasc and Savinasc by Nova Industries A/S and Maxatasc by International

-19-

Biosynthetics, Inc. Desirably the enzymes are present in the composition in an amount of from 0.5 to 3 wt%, especially 1 to 2 wt%.

5 The composition may, if desired, comprise a thickening agent or gelling agent. Suitable thickeners are polyacrylate polymers such as those sold under the trade mark CARBOPOL, or the trade mark ACUSOL by Rohm and Hass Company. Other suitable thickeners are xanthan
10 gums. The thickener, if present, is generally present in an amount of from 0.2 to 4 wt%, especially 0.5 to 2 wt%.

Dishwasher compositions usually comprise a detergency builder. Suitable builders are alkali metal
15 or ammonium phosphates, polyphosphates, phosphonates, polyphosphonates, carbonates, bicarbonates, borates, polyhydroxysulfonates, polyacetates, carboxylates such as citrates, and polycarboxylates. The builder is desirably present in an amount of up to 90 wt%, preferably 15 to 90
20 wt%, more preferable 15 to 75 wt%, relative to the total weight of the composition. Further details of suitable components are given in, for example, EP-A-694,059, EP-A-518,720 and WO 99/06522.

25 The compositions can also optionally comprise one or more additional ingredients. These include conventional detergent composition components such as further surfactants, bleaches, bleach enhancing agents, builders, suds boosters or suds suppressors, anti-tarnish and anti-
30 corrosion agents, organic solvents, co-solvents, phase stabilisers, emulsifying agents, preservatives, soil suspending agents, soil release agents, germicides, pH

-20-

adjusting agents or buffers, non-builder alkalinity sources, chelating agents, clays such as smectite clays, enzyme stabilizers, anti-limescale agents, colourants, dyes, hydrotropes, dye transfer inhibiting agents, brighteners, and perfumes. If used, such optional ingredients will generally constitute no more than 10 wt%, for example from 1 to 6 wt%, the total weight of the compositions.

10 The builders counteract the effects of calcium, or other ion, water hardness encountered during laundering or bleaching use of the compositions herein. Examples of such materials are citrate, succinate, malonate, carboxymethyl succinate, carboxylate, polycarboxylate and
15 polyacetyl carboxylate salts, for example with alkali metal or alkaline earth metal cations, or the corresponding free acids. Specific examples are sodium, potassium and lithium salts of oxydisuccinic acid, mellitic acid, benzene polycarboxylic acids, C₁₀-C₂₂ fatty
20 acids and citric acid. Other examples are organic phosphonate type sequestering agents such as those sold by Monsanto under the trade mark Dequest and alkylhydroxy phosphonates. Citrate salts and C₁₂-C₁₈ fatty acid soaps are preferred.

25

Other suitable builders are polymers and copolymers known to have builder properties. For example, such materials include appropriate polyacrylic acid, polymaleic acid, and polyacrylic/polymaleic and
30 copolymers and their salts, such as those sold by BASF under the trade mark Sokalan.

-21-

The builders generally constitute from 0 to 3 wt%, more preferably from 0.1 to 1 wt%, by weight of the compositions.

5 Compositions which comprise an enzyme may optionally contain materials which maintain the stability of the enzyme. Such enzyme stabilizers include, for example, polyols such as propylene glycol, boric acid and borax. Combinations of these enzyme stabilizers may also be
10 employed. If utilized, the enzyme stabilizers generally constitute from 0.1 to 1 wt% of the compositions.

The compositions may optionally comprise materials which serve as phase stabilizers and/or co-solvents.
15 Example are C₁-C₃ alcohols such as methanol, ethanol and propanol. C₁-C₃ alkanolamines such as mono-, di- and triethanolamines can also be used, by themselves or in combination with the alcohols. The phase stabilizers and/or co-solvents can, for example, constitute 0 to 1
20 wt%, preferably 0.1 to 0.5 wt%, of the composition.

The compositions may optionally comprise components which adjust or maintain the pH of the compositions at optimum levels. The pH may be from, for example, 1 to
25 13, such as 8 to 11 depending on the nature of the composition. For example a dishwashing composition desirably has a pH of 8 to 11, a laundry composition desirable has a pH of 7 to 9, and a water-softening composition desirably has a pH of 7 to 9. Examples of pH
30 adjusting agents are NaOH and citric acid.

-22-

The containers may themselves be packaged in outer containers if desired, for example non-water soluble containers from which the water-soluble containers are removed before use.

-23-

CLAIMS

1. A process for cutting or perforating a water-soluble or water-dispersible film or stack of films in the form of a web comprising a plurality of compartments by which each compartment is cut or perforated by applying a laser beam to the film or stack of films.

2. A process according to claim 1 wherein the water-soluble film is based upon PVOH.

3. A process according to claim 1 or 2 wherein the film is in the form of a laminate.

4. A process according to any one of claims 1 to 3 wherein the film is perforated by the laser beam.

5. A process according to any one of the preceding claims wherein the film has a thickness of from 20 to 150 μm and the stack of films has a thickness of from 40 to 500 μm .

6. A process for producing a water-soluble or water-dispersible container containing a composition which comprises:

- a. producing a base web water-soluble or water-dispersible film containing a plurality of pockets;
- b. filling each pocket with a composition;
- c. sealing the pockets with a top web water-soluble or water-dispersible film to produce closed containers; and

-24-

d. separating at least one container from the plurality of containers by cutting or perforating the combined web with a laser beam.

5 7. A process according to claim 6 wherein the composition is a liquid composition.

8. A process according to any one of the preceding claims wherein the composition is a fabric care, surface
10 care or dishwashing composition.

9. A process according to claim 8 wherein the composition is a dishwashing, water-softening, laundry or detergent composition or a rinse-aid.

15 10. A process according to claim 8 wherein the composition is a disinfectant, antibacterial or antiseptic composition, or a refill composition for a trigger-type spray.

20 11. A process according to any one of claims 1 to 6 wherein the composition is a hazardous composition which is potentially toxic or damaging or detrimental to health or the environment.

25 12. A process according to any one of claims 1 to 6 wherein the composition is a pesticidal composition.

30 13. A process according to any one of claims 1 to 6 wherein the composition is a pharmaceutical or nutraceutical composition.

-25-

14. Use of a laser beam to continuously cut or perforate a PVOH film.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 03/00276

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 B65D65/46 B23K26/40

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 7 B65D B23K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

WPI Data, EPO-Internal, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 699 586 A (NAT STARCH CHEM INVEST) 6 March 1996 (1996-03-06) column 2, line 46 - line 49 column 3, line 2 - line 3 column 4, line 16 - line 17 column 4, line 34 column 5, line 10 - line 14 column 4, line 54 - line 59 column 6, line 36 - line 45; claims 3-5; figure 1	1-3, 5-7, 11, 14
X	PATENT ABSTRACTS OF JAPAN vol. 007, no. 231 (P-229), 13 October 1983 (1983-10-13) & JP 58 121022 A (HITACHI SEISAKUSHO KK), 19 July 1983 (1983-07-19)	14
A	abstract	1-4, 6, 7
	--- -/--	



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *&* document member of the same patent family

Date of the actual completion of the international search

21 May 2003

Date of mailing of the international search report

03/06/2003

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Aran, D

INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 03/00276

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	PATENT ABSTRACTS OF JAPAN vol. 017, no. 649 (E-1468), 2 December 1993 (1993-12-02) & JP 05 211381 A (NEC CORP), 20 August 1993 (1993-08-20)	14
A	abstract	1,6,7
X	US 5 844 200 A (GRAVES JEFFREY ET AL) 1 December 1998 (1998-12-01)	14
A	column 8, line 64 -column 9, line 5	1-4,6
X	US 3 656 988 A (STEFFEN JURG ET AL) 18 April 1972 (1972-04-18)	14
A	column 1, line 8 - line 10 column 2, line 35; figure	1-4,6
A	WO 00 55068 A (UNILEVER PLC ;LEVER HINDUSTAN LTD (IN); UNILEVER NV (NL)) 21 September 2000 (2000-09-21) cited in the application the whole document	1,2,6,7, 9
A	EP 0 518 689 A (RHONE POULENC AGROCHIMIE) 16 December 1992 (1992-12-16) cited in the application the whole document	1,2,6, 11,12,14
A	WO 97 27743 A (ZENECA LTD ;SHAUNAK RICHA (GB); HOLMES PETER (GB); LANDHAM ROWENA) 7 August 1997 (1997-08-07) cited in the application the whole document	1,2,6,7, 11
A	EP 0 518 720 A (COLGATE PALMOLIVE CO) 16 December 1992 (1992-12-16) cited in the application the whole document	9
A	WO 99 06522 A (ADDISON MICHAEL CROMBIE ;ROWLAND BARRY (GB); MCGREGOR ALASDAIR DUN) 11 February 1999 (1999-02-11) cited in the application the whole document	9
A	WO 94 25557 A (PROCTER & GAMBLE) 10 November 1994 (1994-11-10) cited in the application the whole document	9

INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 03/00276

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 0699586	A	06-03-1996	AU 672555 B2	03-10-1996
			AU 2174095 A	18-04-1996
			CA 2154497 A1	13-02-1996
			EP 0699586 A1	06-03-1996
			JP 8092531 A	09-04-1996
			NO 952682 A	13-02-1996
JP 58121022	A	19-07-1983	NONE	
JP 05211381	A	20-08-1993	NONE	
US 5844200	A	01-12-1998	AU 2832697 A	05-12-1997
			WO 9743077 A1	20-11-1997
US 3656988	A	18-04-1972	CH 505676 B	15-04-1971
			CH 510506 B	29-01-1971
			CA 950283 A1	02-07-1974
			DE 2008097 A1	15-10-1970
			FR 2033105 A5	27-11-1970
			GB 1255431 A	01-12-1971
			JP 50030877 B	04-10-1975
			NL 7002652 A	31-08-1970
			US 3742907 A	03-07-1973
			CH 295669 A	29-01-1971
WO 0055068	A	21-09-2000	AU 3425600 A	04-10-2000
			BR 0009049 A	15-01-2002
			CA 2360804 A1	21-09-2000
			CN 1344214 T	10-04-2002
			WO 0055068 A1	21-09-2000
			EP 1161382 A1	12-12-2001
			TR 200102519 T2	21-12-2001
			US 2002033004 A1	21-03-2002
EP 0518689	A	16-12-1992	AP 305 A	28-01-1994
			AT 176988 T	15-03-1999
			AU 655282 B2	15-12-1994
			AU 1802492 A	24-12-1992
			BR 9202348 A	19-01-1993
			CA 2070689 A1	15-12-1992
			CN 1067860 A	13-01-1993
			CS 9201791 A3	16-12-1992
			DE 69228501 D1	08-04-1999
			DE 69228501 T2	02-09-1999
			DK 518689 T3	27-09-1999
			EP 0518689 A1	16-12-1992
			ES 2127742 T3	01-05-1999
			FI 922735 A	15-12-1992
			GR 3029860 T3	30-07-1999
			HU 67202 A2	28-02-1995
			IE 921923 A1	16-12-1992
			IL 102177 A	10-06-1997
			JP 3372965 B2	04-02-2003
			JP 5262388 A	12-10-1993
			MX 9202778 A1	01-12-1992
			PL 294883 A1	22-02-1993
			TR 26091 A	15-12-1994
			US 5341932 A	30-08-1994

INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 03/00276

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0518689	A	ZA 9204315 A	10-03-1993
WO 9727743	A	07-08-1997	
		AU 1385197 A	22-08-1997
		DE 69719013 D1	20-03-2003
		EP 0880316 A1	02-12-1998
		WO 9727743 A1	07-08-1997
		JP 2000504005 T	04-04-2000
		TW 414688 B	11-12-2000
		US 6204223 B1	20-03-2001
EP 0518720	A	16-12-1992	
		AT 127515 T	15-09-1995
		AU 651686 B2	28-07-1994
		AU 1625892 A	03-12-1992
		CA 2069850 A1	01-12-1992
		DE 69204568 D1	12-10-1995
		DE 69204568 T2	15-05-1996
		DK 518720 T3	29-01-1996
		EP 0518720 A1	16-12-1992
		FI 922488 A	01-12-1992
		GR 92100238 A	31-03-1993
		NO 922047 A	01-12-1992
		NZ 242836 A	24-02-1995
		PT 100542 A	30-11-1993
		US 5527483 A	18-06-1996
		US 5618465 A	08-04-1997
		AU 655261 B2	08-12-1994
		AU 1630692 A	03-12-1992
		CA 2069847 A1	01-12-1992
		FI 922490 A	01-12-1992
		GR 92100237 A	31-03-1993
		NO 922049 A	01-12-1992
		NZ 242838 A	24-02-1995
		PT 100540 A	30-11-1993
WO 9906522	A	11-02-1999	
		GB 2327949 A	10-02-1999
		AT 226626 T	15-11-2002
		BR 9815605 A	20-11-2001
		CN 1272875 T	08-11-2000
		DE 29823752 U1	05-01-2000
		DE 29824535 U1	06-09-2001
		DE 69808885 D1	28-11-2002
		DK 960187 T3	24-02-2003
		EP 1134281 A1	19-09-2001
		EP 1162258 A2	12-12-2001
		EP 0960187 A1	01-12-1999
		ES 2142782 T1	01-05-2000
		JP 2001512177 T	21-08-2001
		WO 9906522 A1	11-02-1999
		US 6451754 B1	17-09-2002
WO 9425557	A	10-11-1994	
		CA 2161085 A1	10-11-1994
		EP 0694059 A1	31-01-1996
		ES 2126754 T3	01-04-1999
		WO 9425557 A1	10-11-1994
		US 5591703 A	07-01-1997